

VALOX™ FR RESINS 357XU

REGION EUROPE

DESCRIPTION

VALOX 357XU is an unreinforced, UV stabilized, impact modified flame retardant Polybutylene Terephthalate/Polycarbonate (PBT) injection moldable grade. It has excellent chemical resistance and a UL94V0@0.75mm and 5VA@2.5mm flame rating. This is a good candidate for applications in the electrical industry including bobbins, switches, and enclosures.

TYPICAL PROPERTY VALUES

Revision 20210812

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	50	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	40	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	30	%	ASTM D638
Tensile Modulus, 50 mm/min	2100	MPa	ASTM D638
Taber Abrasion, CS-17, 1 kg	33	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	40	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	30	%	ISO 527
Tensile Modulus, 1 mm/min	2100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2100	MPa	ISO 178
Ball Indentation Hardness, H358/30	113	MPa	ISO 2039-1
Hardness, Rockwell R	115	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	NB	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	NB	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	NB	J/m	ASTM D4812
Izod Impact, notched, 23°C	350	J/m	ASTM D256
Izod Impact, notched, 0°C	170	J/m	ASTM D256
Izod Impact, notched, -30°C	110	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	40	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	14	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	45	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, 23°C	15	kJ/m ²	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	20	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, -30°C	10	kJ/m ²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL			
Vicat Softening Temp, Rate A/50	180	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	145	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	130	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	85	°C	ASTM D648
Thermal Conductivity	0.17	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	1.E-04	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	1.E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	180	°C	ISO 306
Vicat Softening Temp, Rate B/50	145	°C	ISO 306
Vicat Softening Temp, Rate B/120	145	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	135	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	85	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	130	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	85	°C	ISO 75/Af
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.34	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow	1.1 – 1.8	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.9 – 1.8	%	SABIC method
Melt Flow Rate, 265°C/5.0 kgf	18	g/10 min	ASTM D1238
Melt Flow Rate, 266°C/5.0 kgf	18	g/10 min	ASTM D1238
Density	1.34	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.5	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	8	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	15	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	300	Pa-s	ISO 11443
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 0.8 mm	34	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	26	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.9	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.007	-	IEC 60250

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Comparative Tracking Index	200	V	IEC 60112
Comparative Tracking Index, M	100	V	IEC 60112
Relative Permittivity, 50/60 Hz	3	-	IEC 60250
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	0.75	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	2.5	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Oxygen Index (LOI)	30	%	ISO 4589
UV-light, water exposure/immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.